


## N5 - UK Roof and Wall Panel



### Product Information

It has 5 ribs which is lateral connected sandwich panel. Its biggest advantage is that it enables fast assembly thanks to lateral connected panel connection. This product enables wide gaps to be passed safely with its indented form. It has a joint detail with angle.

### Production Plant

UK

### Product Application

- Industrial Buildings
- Military Buildings
- Public Buildings
- Agricultural Buildings
- Sports Facilities
- Construction Site Buildings
- Silos
- Hypermarkets
- Shopping Centers
- Storehouse Halls
- Administrative Buildings

and all other concrete structures with steel or prefabricated load bearing systems.

## Performance Advantages

It has the perfect fire resistance values.

It has a joint detail with angle

Fast and trouble-free installation saves both time and labor.

It has high performance in sound insulation as well as heat insulation.


Thanks to its colorful surface, there is no need for additional coatings such as plaster or paint.

There are surface paint (Polyester, PvdF, Plastisol, PVC) options suitable for the place of use.

Color selection can be made from the RAL catalogue.

It does not deteriorate, rot or mold over time.

## Cross Section



Thickness: 40-50-60-80-100-120-140-160-180-200 mm

<b>Modular Width</b>	1,000 mm
<b>Minimum Length</b>	2 meters
<b>Maximum Length</b>	Depends on transport conditions.

## SmartCore – PIR Properties

<b>Density (EN 1602)</b>	PIR: 40 (± 2) kg/m <sup>3</sup> & SmartCore: 41 (± 2) kg/m <sup>3</sup>
<b>Thickness</b>	40-50-60-80-100-120-140-160-180-200 mm
<b>Thermal Conductivity (EN 13165)</b>	PIR: 0.022-0.024 W/mK & SmartCore: 0.018-0.019 W/mK
<b>Reaction to Fire (13501)</b>	PIR: B-s2,d0 & SmartCore: B-s2,d0

## Thermal Conductivity Table for SmartCore Panels

Panel Thickness	U Thermal Conductivity (W/m <sup>2</sup> K)	R Thermal Resistance (m <sup>2</sup> K/W)	R Thermal Resistance (ft <sup>2</sup> °F h/Btu)
40 mm	0,43	2,350	13,343
50 mm	0,35	2,880	16,353
60 mm	0,29	3,400	19,305
80 mm	0,22	4,460	25,324
100 mm	0,18	5,510	31,286
120 mm	0,15	6,560	37,248
140 mm	0,13	7,610	43,210
160 mm	0,12	8,670	49,228
180 mm	0,10	9,720	55,190
200 mm	0,09	10,770	61,152

According to EN 14509


While every effort has been made to ensure the accuracy of the information provided in this document, Assan Panel and its subsidiaries accept no responsibility for any errors or for content that may be misleading. Any recommendations or descriptions regarding product use or application are offered for general guidance only. Assan Panel and its subsidiaries accept no liability in respect thereof. Assan Panel reserves the right to make changes to this document at any time without prior notice.

### Thermal Conductivity Table for PIR Panels

Panel Thickness	U Thermal Conductivity (W/m <sup>2</sup> K)	R Thermal Resistance (m <sup>2</sup> K/W)	R Thermal Resistance (ft <sup>2</sup> °F h/Btu)
40 mm	0,51	1,970	11,186
50 mm	0,42	2,400	13,627
60 mm	0,35	2,840	16,126
80 mm	0,27	3,710	21,065
100 mm	0,22	4,570	25,948
120 mm	0,18	5,440	30,888
140 mm	0,16	6,310	35,828
160 mm	0,14	7,180	40,768
180 mm	0,12	8,050	45,708
200 mm	0,11	8,920	50,648

According to EN 14509

### Metal Surfaces



### Prepainted Galvanized Steel Surface

<b>Metal Type</b>	h 8 0
<b>External Facing Thickness</b>	50
<b>Internal Facing Thickness</b>	40
<b>Thickness Tolerance (EN 10143)</b>	V
<b>Steel Quality (EN 10327)</b>	oGrade (S220GD+Z, S250GD+Z, S280GD+Z, S320GD+Z, S350GD+Z)
<b>Paint Type</b>	h h 7 h


### Tolerance Values

Panel Length	Panel Thickness	Panel Cover Width	Rectangularity
If L <= 3,000 mm ± 5 mm; If L > 3,000 mm ± 10 mm	D ≤ 100 mm ± 2 mm	± 2 mm for all profiles	s ≤ 0.6% of the nominal cover thickness (w). / (Width x 0.006)

### Standard Package

Thickness (mm)	40	50	60	80	100	120	140	160	180	200
<b>Quantity</b>	20	18	14	10	9	8	7	6	5	4

### Joint Details



NOVA 5 (PIR) ROOF PANEL LOAD SPAN TABLE

Core Thickness (mm)	Load Type kN/m <sup>2</sup>	GdLb <sup>2</sup> Yb <sup>2</sup> h <sup>2</sup> (L) fb L															
		%a	%s	%a	\$\$\$	\$\$\$	\$\$\$	\$\$\$	\$\$\$	\$\$\$	\$\$\$	\$\$\$	\$\$\$	\$\$\$	\$\$\$	\$\$\$	\$\$\$
SINGLE SPAN 	a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	
	Pressure (kN/m <sup>2</sup> )	2,75	2,09	1,67	1,38	1,16	1,16	0,87	0,76	0,67	0,51	0,39	0,30	-	-	-	
	Suction (kN/m <sup>2</sup> )	-4,21	-3,31	-2,46	-1,80	-1,39	-1,11	-0,92	-0,77	-0,66	-0,57	-0,50	-0,44	-	-	-	
	b (mm)	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	
	a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	
	Pressure (kN/m <sup>2</sup> )	3,03	2,35	1,92	1,61	1,37	1,19	1,04	0,93	0,82	0,73	0,60	0,47	0,37	0,29	-	-
	Suction (kN/m <sup>2</sup> )	-4,87	-3,91	-2,84	-2,10	-1,62	-1,30	-1,06	-0,90	-0,77	-0,67	-0,59	-0,52	-0,47	-0,42	-	-
	b (mm)	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60
	a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40
	Pressure (kN/m <sup>2</sup> )	3,31	2,62	2,16	1,84	1,59	1,39	1,23	1,09	0,99	0,89	0,80	0,67	0,54	0,44	0,35	0,28
	Suction (kN/m <sup>2</sup> )	-5,55	-4,42	-3,22	-2,39	-1,85	-1,49	-1,22	-1,03	-0,89	-0,77	-0,67	-0,60	-0,54	-0,48	-0,44	-0,40
	b (mm)	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60
a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	
Pressure (kN/m <sup>2</sup> )	3,87	3,15	2,66	2,31	2,03	1,81	1,62	1,45	1,31	1,19	1,08	0,99	0,90	0,79	0,66	0,55	
Suction (kN/m <sup>2</sup> )	-6,64	-5,11	-3,99	-2,98	-2,32	-1,87	-1,54	-1,29	-1,11	-0,97	-0,85	-0,75	-0,67	-0,61	-0,55	-0,50	
b (mm)	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	
a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	
Pressure (kN/m <sup>2</sup> )	4,43	3,68	3,17	2,79	2,48	2,23	2,02	1,83	1,66	1,51	1,38	1,26	1,15	1,05	0,98	0,87	
Suction (kN/m <sup>2</sup> )	-7,51	-5,83	-4,76	-3,57	-2,79	-2,25	-1,85	-1,56	-1,33	-1,16	-1,01	-0,91	-0,81	-0,73	-0,66	-0,60	
b (mm)	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	
a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	
Pressure (kN/m <sup>2</sup> )	4,99	4,21	3,68	3,27	2,94	2,66	2,42	2,21	2,01	1,84	1,68	1,54	1,42	1,30	1,20	1,10	
Suction (kN/m <sup>2</sup> )	-8,40	-6,57	-5,40	-4,16	-3,26	-2,63	-2,17	-1,83	-1,56	-1,35	-1,19	-1,05	-0,95	-0,85	-0,77	-0,70	
b (mm)	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	
a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	
Pressure (kN/m <sup>2</sup> )	5,83	5,02	4,45	4,01	3,64	3,32	3,04	2,78	2,55	2,35	2,16	1,98	1,83	1,68	1,55	1,44	
Suction (kN/m <sup>2</sup> )	-9,75	-7,69	-6,35	-5,05	-3,96	-3,20	-2,64	-2,23	-1,90	-1,65	-1,44	-1,28	-1,14	-1,03	-0,94	-0,85	
b (mm)	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	
a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	
Pressure (kN/m <sup>2</sup> )	6,38	5,56	4,97	4,50	4,11	3,76	3,45	3,17	2,92	2,69	2,47	2,28	2,10	1,94	1,79	1,66	
Suction (kN/m <sup>2</sup> )	-10,67	-8,45	-7,00	-5,64	-4,43	-3,58	-2,96	-2,49	-2,13	-1,85	-1,62	-1,43	-1,28	-1,15	-1,04	-0,95	
b (mm)	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	

7 crY H W b Ygg fb a L	@UKHndY_Bm	GdLb <sup>2</sup> Yb <sup>2</sup> h <sup>2</sup> (L) fb L															
		%a	%s	%a	\$\$\$	\$\$\$	\$\$\$	\$\$\$	\$\$\$	\$\$\$	\$\$\$	\$\$\$	\$\$\$	\$\$\$	\$\$\$	\$\$\$	\$\$\$
DOUBLE SPAN 	a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	
	Pressure (kN/m <sup>2</sup> )	2,75	2,09	1,67	1,38	1,16	0,97	0,81	0,69	0,59	-	-	-	-	-	-	
	Suction (kN/m <sup>2</sup> )	-4,16	-3,06	-2,38	-1,80	-1,39	-1,11	-0,92	-0,77	-0,66	-	-	-	-	-	-	
	b (mm)	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	
	a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	
	Pressure (kN/m <sup>2</sup> )	3,03	2,35	1,92	1,53	1,23	1,02	0,87	0,74	0,64	0,56	-	-	-	-	-	
	Suction (kN/m <sup>2</sup> )	-4,87	-3,91	-2,84	-2,10	-1,62	-1,30	-1,06	-0,90	-0,77	-0,67	-	-	-	-	-	
	b (mm)	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	
	a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	
	Pressure (kN/m <sup>2</sup> )	3,31	2,62	2,04	1,60	1,30	1,08	0,93	0,80	0,69	0,60	-	-	-	-	-	
	Suction (kN/m <sup>2</sup> )	-4,68	-3,51	-2,76	-2,26	-1,85	-1,49	-1,22	-1,03	-0,89	-0,77	-	-	-	-	-	
	b (mm)	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	
	a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	
	Pressure (kN/m <sup>2</sup> )	3,87	2,89	2,20	1,75	1,43	1,20	1,02	0,89	0,78	0,68	0,60	0,54	-	-	-	
	Suction (kN/m <sup>2</sup> )	-5,17	-3,92	-3,12	-2,56	-2,16	-1,86	-1,54	-1,29	-1,11	-0,97	-0,85	-0,75	-	-	-	
	b (mm)	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	
	a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	
	Pressure (kN/m <sup>2</sup> )	4,21	3,07	2,36	1,89	1,56	1,31	1,12	0,98	0,86	0,76	0,67	0,60	0,54	-	-	
	Suction (kN/m <sup>2</sup> )	-5,63	-4,31	-3,45	-2,85	-2,41	-2,08	-1,82	-1,56	-1,33	-1,16	-1,01	-0,91	-0,81	-	-	
	b (mm)	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	
	a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	
	Pressure (kN/m <sup>2</sup> )	4,41	3,24	2,51	2,02	1,67	1,41	1,21	1,05	0,94	0,83	0,74	0,66	0,59	0,54	-	
	Suction (kN/m <sup>2</sup> )	-6,06	-4,68	-3,77	-3,12	-2,65	-2,29	-2,01	-1,79	-1,56	-1,35	-1,19	-1,05	-0,95	-0,85	-	
	b (mm)	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	
a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40		
Pressure (kN/m <sup>2</sup> )	4,69	3,49	2,73	2,21	1,84	1,56	1,34	1,17	1,02	0,93	0,83	0,74	0,67	0,61	0,55		
Suction (kN/m <sup>2</sup> )	-6,66	-5,19	-4,21	-3,50	-2,99	-2,59	-2,28	-2,03	-1,82	-1,65	-1,44	-1,28	-1,14	-1,03	-0,94		
b (mm)	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60		
a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40		
Pressure (kN/m <sup>2</sup> )	4,87	3,64	2,86	2,33	1,94	1,65	1,42	1,24	1,09	0,99	0,88	0,79	0,71	0,65	0,59		
Suction (kN/m <sup>2</sup> )	-7,04	-5,51	-4,48	-3,74	-3,20	-2,77	-2,44	-2,18	-1,96	-1,78	-1,62	-1,43	-1,28	-1,15	-1,04		
b (mm)	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60		


7 crY H W b Ygg fb a L	@UKHndY_Bm	GdLb <sup>2</sup> Yb <sup>2</sup> h <sup>2</sup> (L) fb L															
		%a	%s	%a	\$\$\$	\$\$\$	\$\$\$	\$\$\$	\$\$\$	\$\$\$	\$\$\$	\$\$\$	\$\$\$	\$\$\$	\$\$\$	\$\$\$	\$\$\$
TRIPLE SPAN 	a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	
	Pressure (kN/m <sup>2</sup> )	2,75	2,09	1,67	1,38	1,16	1,16	0,87	0,76	0,67	0,59	0,52	0,46	0,41	0,37	-	
	Suction (kN/m <sup>2</sup> )	-4,21	-3,31	-2,46	-1,80	-1,39	-1,11	-0,92	-0,77	-0,66	-0,57	-0,50	-0,44	-0,40	-0,36	-	
	b (mm)	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	
	a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	
	Pressure (kN/m <sup>2</sup> )	3,03	2,35	1,92	1,61	1,37	1,19	1,04	0,92	0,80	0,70	0,62	0,55	0,49	0,44	-	
	Suction (kN/m <sup>2</sup> )	-4,87	-3,82	-2,84	-2,10	-1,62	-1,30	-1,06	-0,90	-0,77	-0,67	-0,59	-0,52	-0,47	-0,42	-	
	b (mm)	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	
	a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	
	Pressure (kN/m <sup>2</sup> )	3,31	2,62	2,16	1,84	1,58	1,32	1,12	0,98	0,85	0,75	0,66	0,59	0,53	0,47	0,43	
	Suction (kN/m <sup>2</sup> )	-5,36	-4,02	-3,18	-2,39	-1,85	-1,49	-1,22	-1,03	-0,89	-0,77	-0,67	-0,60	-0,54	-0,48	-0,44	
	b (mm)	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	
	a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	
	Pressure (kN/m <sup>2</sup> )	3,87	3,15	2,62	2,08	1,70	1,43	1,22	1,05	0,94	0,83	0,74	0,66	0,59	0,54	0,49	
	Suction (kN/m <sup>2</sup> )	-5,81	-4,41	-3,52	-2,91	-2,32	-1,87	-1,54	-1,29	-1,11	-0,97	-0,85	-0,75	-0,67	-0,61	-0,55	
	b (mm)	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	
	a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	
	Pressure (kN/m <sup>2</sup> )	4,43	3,59	2,76	2,21	1,82	1,53	1,									

NOVA 5 (PIR) WALL PANEL LOAD SPAN TABLE

Core Thickness (mm)	Load Type kN/m <sup>2</sup>	GdLb <sup>2</sup> Yb <sup>2</sup> h <sup>2</sup> (L) fb L															
		%a	%s	%a	δSS	δB	δS	δA	'SS	'B	'S	'A	(SS)	(B)	(S)	(A)	'SS
40	a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	
	Pressure (kN/m <sup>2</sup> )	3.22	2.39	1.90	1.57	1.34	1.17	1.03	0.94	0.85	0.78	0.72	0.66	0.59	0.53	-	
	Suction (kN/m <sup>2</sup> )	-4.15	-3.25	-2.43	-1.77	-1.35	-1.07	-0.88	-0.73	-0.61	-0.52	-0.45	-0.39	-0.35	-0.31	-	
	b (mm)	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	
	Pressure (kN/m <sup>2</sup> )	3.80	2.86	2.28	1.90	1.63	1.42	1.26	1.14	1.03	0.96	0.88	0.82	0.75	0.68	0.61	
	Suction (kN/m <sup>2</sup> )	-4.81	-3.84	-2.81	-2.06	-1.58	-1.25	-1.02	-0.86	-0.72	-0.62	-0.53	-0.47	-0.41	-0.37	-0.33	
	a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	
	Pressure (kN/m <sup>2</sup> )	4.36	3.30	2.66	2.22	1.91	1.67	1.49	1.34	1.22	1.12	1.03	0.97	0.91	0.83	0.75	
	Suction (kN/m <sup>2</sup> )	-5.48	-4.40	-3.19	-2.35	-1.81	-1.44	-1.17	-0.99	-0.83	-0.71	-0.62	-0.54	-0.48	-0.42	-0.38	
	b (mm)	66	60	60	60	60	60	60	60	60	60	60	60	60	60	60	
	Pressure (kN/m <sup>2</sup> )	5.42	4.17	3.38	2.84	2.45	2.16	1.92	1.74	1.58	1.45	1.34	1.25	1.17	1.10	1.03	
	Suction (kN/m <sup>2</sup> )	-6.62	-5.08	-3.95	-2.94	-2.27	-1.81	-1.48	-1.24	-1.05	-0.91	-0.79	-0.69	-0.61	-0.54	-0.48	
a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40		
Pressure (kN/m <sup>2</sup> )	6.44	5.00	4.08	3.45	2.99	2.63	2.35	2.13	1.94	1.79	1.65	1.54	1.44	1.35	1.27		
Suction (kN/m <sup>2</sup> )	-7.48	-5.80	-4.71	-3.52	-2.74	-2.19	-1.79	-1.50	-1.27	-1.09	-0.95	-0.84	-0.74	-0.66	-0.59		
b (mm)	80	60	60	60	60	60	60	60	60	60	60	60	60	60	60		
Pressure (kN/m <sup>2</sup> )	7.44	5.82	4.77	4.05	3.51	3.10	2.78	2.51	2.30	2.11	1.96	1.82	1.71	1.60	1.51		
Suction (kN/m <sup>2</sup> )	-8.37	-6.54	-5.36	-4.11	-3.20	-2.56	-2.10	-1.76	-1.49	-1.28	-1.11	-0.98	-0.87	-0.77	-0.69		
a (mm)	45	42	41	40	40	40	40	40	40	40	40	40	40	40	40		
Pressure (kN/m <sup>2</sup> )	8.91	7.02	5.79	4.93	4.29	3.80	3.41	3.09	2.82	2.60	2.41	2.25	2.10	1.98	1.87		
Suction (kN/m <sup>2</sup> )	-9.72	-7.66	-6.31	-4.98	-3.89	-3.13	-2.57	-2.15	-1.82	-1.57	-1.36	-1.19	-1.05	-0.95	-0.85		
b (mm)	90	60	60	60	60	60	60	60	60	60	60	60	60	60	60		
Pressure (kN/m <sup>2</sup> )	9.88	7.82	6.47	5.51	4.81	4.28	3.82	3.47	3.17	2.92	2.71	2.53	2.37	2.23	2.10		
Suction (kN/m <sup>2</sup> )	-10.63	-8.41	-6.95	-5.57	-4.36	-3.50	-2.88	-2.41	-2.04	-1.76	-1.53	-1.34	-1.18	-1.05	-0.96		



7 c1Y H <sup>2</sup> W <sup>2</sup> b <sup>2</sup> Yg <sup>2</sup> fb a L	@UKHndY <sup>2</sup> Bm <sup>2</sup>	GdLb <sup>2</sup> Yb <sup>2</sup> h <sup>2</sup> (L) fb L															
		%a	%s	%a	δSS	δB	δS	δA	'SS	'B	'S	'A	(SS)	(B)	(S)	(A)	'SS
40	a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	
	Pressure (kN/m <sup>2</sup> )	3.22	2.39	1.90	1.57	1.34	1.17	1.03	0.70	0.41	0.23	-	-	-	-	-	
	Suction (kN/m <sup>2</sup> )	-3.55	-2.53	-1.91	-1.50	-1.22	-1.02	-0.88	-0.73	-0.61	-	-	-	-	-	-	
	b (mm)	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	
	Pressure (kN/m <sup>2</sup> )	3.80	2.86	2.28	1.90	1.63	1.42	1.26	0.98	0.58	0.34	0.20	-	-	-	-	
	Suction (kN/m <sup>2</sup> )	-3.80	-2.73	-2.08	-1.65	-1.34	-1.13	-0.98	-0.85	-0.72	-0.62	-	-	-	-	-	
	a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	
	Pressure (kN/m <sup>2</sup> )	4.36	3.30	2.66	2.22	1.88	1.59	1.20	0.80	0.48	0.29	0.16	-	-	-	-	
	Suction (kN/m <sup>2</sup> )	-4.04	-2.93	-2.24	-1.78	-1.46	-1.23	-1.05	-0.93	-0.82	-0.71	-0.62	-	-	-	-	
	b (mm)	66	60	60	60	60	60	60	60	60	60	60	60	60	60	60	
	Pressure (kN/m <sup>2</sup> )	5.41	4.05	3.18	2.58	2.15	1.83	1.58	1.24	0.86	0.54	0.34	0.20	-	-	-	
	Suction (kN/m <sup>2</sup> )	-4.51	-3.31	-2.56	-2.05	-1.69	-1.42	-1.22	-1.06	-0.96	-0.86	-0.77	-0.69	-	-	-	
b (mm)	81	70	63	60	60	60	60	60	60	60	60	60	60	60	60		
a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40		
Pressure (kN/m <sup>2</sup> )	5.90	4.47	3.53	2.89	2.41	2.06	1.78	1.57	1.23	0.88	0.58	0.37	0.23	-	-		
Suction (kN/m <sup>2</sup> )	-4.95	-3.68	-2.86	-2.30	-1.90	-1.61	-1.38	-1.21	-1.07	-0.97	-0.88	-0.80	-0.73	-	-		
b (mm)	88	78	70	64	60	60	60	60	60	60	60	60	60	60	60		
a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40		
Pressure (kN/m <sup>2</sup> )	6.36	4.86	3.87	3.17	2.66	2.28	1.98	1.74	1.54	1.20	0.88	0.60	0.40	0.26	-		
Suction (kN/m <sup>2</sup> )	-5.36	-4.02	-3.15	-2.55	-2.11	-1.79	-1.54	-1.34	-1.19	-1.06	-0.98	-0.89	-0.81	-0.75	-		
b (mm)	97	87	79	72	67	62	60	60	60	60	60	60	60	60	60		
a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40		
Pressure (kN/m <sup>2</sup> )	7.01	5.40	4.33	3.57	3.01	2.58	2.24	1.98	1.76	1.58	1.35	1.15	0.71	0.49	0.34		
Suction (kN/m <sup>2</sup> )	-5.95	-4.51	-3.56	-2.89	-2.41	-2.04	-1.76	-1.54	-1.36	-1.22	-1.10	-1.00	-0.93	-0.86	-0.79		
b (mm)	109	99	91	84	79	74	69	66	63	61	60	60	60	60	60		
a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40		
Pressure (kN/m <sup>2</sup> )	7.42	5.75	4.62	3.82	3.23	2.77	2.42	2.13	1.90	1.71	1.55	1.25	0.97	0.69	0.48		
Suction (kN/m <sup>2</sup> )	-6.31	-4.81	-3.81	-3.11	-2.59	-2.20	-1.90	-1.66	-1.47	-1.32	-1.19	-1.08	-1.08	-0.93	-0.86		
b (mm)	117	107	99	92	86	81	77	73	70	67	64	60	60	60	60		



7 c1Y H <sup>2</sup> W <sup>2</sup> b <sup>2</sup> Yg <sup>2</sup> fb a L	@UKHndY <sup>2</sup> Bm <sup>2</sup>	GdLb <sup>2</sup> Yb <sup>2</sup> h <sup>2</sup> (L) fb L															
		%a	%s	%a	δSS	δB	δS	δA	'SS	'B	'S	'A	(SS)	(B)	(S)	(A)	'SS
40	a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	
	Pressure (kN/m <sup>2</sup> )	3.22	2.39	1.90	1.57	1.34	1.17	1.03	0.98	0.70	0.51	0.39	0.30	0.24	-	-	
	Suction (kN/m <sup>2</sup> )	-4.15	-3.11	-2.39	-1.77	-1.35	-1.07	-0.88	-0.73	-0.61	-0.52	-0.45	-0.39	-	-	-	
	b (mm)	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	
	Pressure (kN/m <sup>2</sup> )	3.80	2.86	2.28	1.90	1.63	1.42	1.26	1.07	0.85	0.62	0.47	0.36	0.28	0.23	0.19	
	Suction (kN/m <sup>2</sup> )	-4.51	-3.29	-2.55	-2.06	-1.58	-1.25	-1.02	-0.86	-0.72	-0.62	-0.53	-0.47	-0.41	-0.37	-	
	a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	
	Pressure (kN/m <sup>2</sup> )	4.36	3.30	2.66	2.22	1.91	1.67	1.32	1.32	0.75	0.56	0.43	0.34	0.27	0.22	-	
	Suction (kN/m <sup>2</sup> )	-4.73	-3.48	-2.70	-2.19	-1.81	-1.44	-1.17	-0.99	-0.83	-0.71	-0.62	-0.54	-0.48	-0.42	-	
	b (mm)	66	60	60	60	60	60	60	60	60	60	60	60	60	60	60	
	Pressure (kN/m <sup>2</sup> )	5.42	4.16	3.38	2.84	2.45	2.16	1.88	1.32	1.32	0.78	0.60	0.47	0.37	0.30	0.24	
	Suction (kN/m <sup>2</sup> )	-5.15	-3.82	-3.00	-2.45	-2.05	-1.76	-1.48	-1.24	-1.05	-0.91	-0.79	-0.69	-0.61	-0.54	-0.48	
b (mm)	81	73	68	64	62	60	60	60	60	60	60	60	60	60	60		
a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40		
Pressure (kN/m <sup>2</sup> )	6.44	4.98	3.96	3.27	2.76	2.38	2.09	1.81	1.28	1.28	0.80	0.62	0.49	0.40	0.32		
Suction (kN/m <sup>2</sup> )	-5.55	-4.16	-3.28	-2.69	-2.26	-1.95	-1.70	-1.50	-1.27	-1.09	-0.95	-0.84	-0.74	-0.66	-0.59		
b (mm)	98	90	81	75	70	66	63	60	60	60	60	60	60	60	60		
a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40		
Pressure (kN/m <sup>2</sup> )	7.00	5.34	4.27	3.53	3.00	2.59	2.28	2.02	1.70	1.24	1.24	0.80	0.63	0.51	0.41		
Suction (kN/m <sup>2</sup> )	-5.94	-4.47	-3.55	-2.91	-2.46	-2.12	-1.86	-1.65	-1.48	-1.28	-1.11	-0.98	-0.87	-0.77	-0.69		
b (mm)	109	98	90	83	78	74	71	68	60	60	60	60	60	60	60		
a (mm)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40		
Pressure (kN/m <sup>2</sup> )	7.62	5.85	4.71	3.91	3.33	2.89	2.54	2.26	2.04	1.77	1.32	1.32	0.88	0.71	0.57		
Suction (kN/m <sup>2</sup> )	-6.49	-4.93	-3.92	-3.24	-2.74	-2.36	-2.07	-1.84	-1.66	-1.50	-1.36	-1.19	-1.05	-0.95	-0.85		
b (mm)	121	110	101	95	90	86	82	79	77	70	60	60	60	60	60		
a (mm)	43	41	40	40	40	40	40	40	40	40	40	40	40	40	40		
Pressure (kN/m <sup>2</sup> )	8.00	6.18	4.99	4.15	3.54	3.07	2.71	2.41	2.17	1.97	1.63	1.24	1				